

LOCTITE HC 9872.1 AERO

Syntactic Film

(KNOWN AS SynCore[®] HC 9872.1)

INTRODUCTION

LOCTITE HC 9872.1 AERO is a toughened 350°F/177°C curing epoxy, low density syntactic core material with superior moisture resistance. LOCTITE HC 9872.1 AERO is co-curable with a wide variety of 350°F/177°C curing epoxy prepreg systems. LOCTITE HC 9872.1 AERO is supplied as a continuous film of controlled thickness, width, and density.

FEATURES

- Excellent Moisture Resistance
- Lightweight Syntactic Core Material
- Modified Epoxy
- 350°F/177°C Cure
- Co-curable with prepregs

Product Forms

	<u>inches</u>	<u>mm</u>
Typical Film Thickness:	0.010 to 0.060 ± 0.002 0.070 to 0.120 ± 0.004	0.254 to 1.524 ± 0.051 1.778 to 3.048 ± 0.102

Film Widths: Standard 12 inches (30.6 cm); other widths may be available as special order

Roll Lengths: Up to 200 feet (61 m) depending on film thickness

Reinforcing Carriers: Supplied with a lightweight non-woven Kevlar[®] Mat reinforcing carrier

Handling

This product is in film form and is ready to use as received. Syntactic film should be removed from cold storage and allowed to warm to room temperature (77°F/25°C) before removing the protective packaging. Syntactic film has protective liners on it which must be removed prior to parts assembly (see "Applying" below). The liners will always be a contrasting color from the syntactic film to allow the user easy confirmation of removal.

Syntactic film in excess of 40 mils on roll stocks is inclined to form wrinkles due to natural tensions encountered during the winding operation. If roll stock is being used and wrinkles are encountered, we recommend removing the film material from the roll and letting it relax for a period of 24 to 48 hours at room temperature. Once material is cut from the roll, the balance of the material on the roll should be taped tightly to prevent the balance of the roll from relaxing.

Application

Storage Life - LOCTITE HC 9872.1 AERO requires refrigerated storage. Store @ 0°F/-18°C or below for maximum storage life. Warranty life @ 0°F/-18°C or below is greater than 12 months. Store in sealed desiccated polyethylene bag provided. Allow adequate time for the container to warm to room temperature before opening for use.



LOCTITE HC 9872.1 AERO

Syntactic Film

(KNOWN AS SynCore® HC 9872.1)

Applying - Syntactic film is a pliable film with tack and drape. Syntactic film can be cut to any desired shape using ordinary razor knives or scissors. Razor knives with templates as guides work best. After cutting the syntactic film, remove the polyethylene release film by peeling it back from a corner. For thin syntactic films, a slight rub with dry ice on the polyethylene will assist in releasing the film from the syntactic film. Apply the syntactic film to the prepreg lay-up. Because of syntactic film's tack, all it takes is a light amount of pressure to secure the edge of the syntactic film to the prepreg stack. A Teflon tool is recommended to smooth the film. This tacks the syntactic film in place and prevents air entrapment. After syntactic film is applied to prepreg lay-up, remove the coated release paper.

Henkel recommends trimming the syntactic film back about half an inch from the edge or damming the edge of the laminate to restrict resin flow.

Open Assembly Time - LOCTITE HC 9872.1 AERO may be used within the following schedule after removing from cold storage:

- @ 77°F/25°C at least 15 days
- @ 90°F/32°C at least 10 days

Curing - In general, LOCTITE HC 9872.1 AERO is cured successfully using the cure cycle and bagging procedures recommended for co-curing epoxy prepreg systems.

Cleanup - Little cleanup should be required. However, uncured syntactic film may be removed effectively with ketone solvents in well ventilated areas. Saturate cloth or industrial wipes with solvent and apply just enough to do the job. Avoid contaminating uncured parts with spray or spillage. Wear respirators equipped with organic vapor cartridges, impervious rubber gloves, and safety goggles when handling solvents. Consult solvent container labels for skin and flammability warnings.

Typical Physical Performance Properties

Typical Uncured Properties

Gel time @ 350°F/177°C:	5-15 minutes
Volatiles @ 350°F/177°C, 60 min:	1% by weight maximum
Flexibility @ 77°F/25°C:	pliable and drapable
Working life @ 77°F/25°C:	15 days
Flow at 50 psi/0.34 MPa, 350°F/177°C:	25-50%

Typical Cured Properties

Density, maximum (ASTM D792):	<u>lb/ft³</u>	<u>kg/m³</u>
for film 0.020 inch (0.508 mm) or less	49	785
for film 0.030 inch (0.762 mm) or greater	42	673

Coefficient of Thermal Expansion:	52 µm/m°C before T _g (190°C)
	220 µm/m°C after T _g (190°C)

Moisture absorption after immersion in 160°F/71°C water at equilibrium - 7% gain



LOCTITE HC 9872.1 AERO

Syntactic Film

(KNOWN AS SynCore[®] HC 9872.1)

Typical Mechanical Performance Properties**Tensile Properties (ASTM D638), Dry Testing**

<u>Test Temperature, °F/°C</u>	Strength		Modulus		Elongation
	<u>psi</u>	<u>MPa</u>	<u>psi</u>	<u>MPa</u>	<u>%</u>
-67/-55	4,700	32.4	-	-	-
77/25	4,800	33.1	400,000	2,758	1.24
180/82	4,000	27.6	320,000	2,206	1.26
350/177	3,300	22.8	240,000	1,655	1.77

Compressive Strength (ASTM D695)

<u>Test Temperature, °F/°C</u>	Dry		Wet¹	
	<u>psi</u>	<u>MPa</u>	<u>psi</u>	<u>MPa</u>
-67/-55	10,500	72.4	-	-
77/25	8,800	60.7	6,800	46.9
180/82	7,000	48.3	6,000	41.4
350/177	5,200	35.9	1,500	10.3

Compressive Modulus

<u>Test Temperature, °F/°C</u>	<u>psi</u>	<u>MPa</u>
77/25	375,000	2,586

Shear Strength² (ASTM D2344)

<u>Test Temperature, °F/°C</u>	Dry		Wet¹	
	<u>psi</u>	<u>MPa</u>	<u>psi</u>	<u>MPa</u>
-67/-55	6,000	41.4	-	-
77/25	6,800	46.9	4,500	31.0
180/82	5,000	34.5	4,000	27.6
350/177	3,100	21.4	2,200	15.2

Shear Modulus³

<u>Test Temperature, °F/°C</u>	<u>psi</u>	<u>MPa</u>
-67/-55	167,000	1,151
77/25	150,000	1,034
180/82	115,000	793
350/177	100,000	689

LOCTITE HC 9872.1 AERO

Syntactic Film

(KNOWN AS SynCore[®] HC 9872.1)

Flatwise Tensile Strength (ASTM C297)

<u>Test Temperature, °F/°C</u>	Dry		Wet ¹	
	<u>psi</u>	<u>MPa</u>	<u>psi</u>	<u>MPa</u>
-67/-55	3,000	20.7	-	-
77/25	3,300	22.8	-	-
180/82	2,800	19.3	2,800	19.3
300/150	2,500	17.2	-	-
350/177	2,400	16.5	-	-

Note:

1. Wet conditioning was attained by exposing the specimens to 95-100% relative humidity at 160°F/ 71°C for 31 days.
2. Sandwich panel made with 3 plies of DMS 2288 Type 1, Class 1 prepreg on each side of the syntactic film.
3. Based on calculated results.

Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood. For industrial use only.

DISPOSAL INFORMATION

Dispose of spent remover and paint residue per local, state and regional regulations. Refer to HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.

PRECAUTIONARY INFORMATION**General:**

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling.

Before using this product refer to container label and HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.



LOCTITE HC 9872.1 AERO

Syntactic Film

(KNOWN AS SynCore® HC 9872.1)

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Rev. 9/2013

Henkel Corporation Aerospace | 2850 Willow Pass Road | Bay Point, CA 94565
PHONE: +1.925.458.8000 | FAX: +1.925.458.8030 | www.henkel.com/aerospace

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

