



# Plastilock® 795-SF

## Epoxy Film Adhesive

Henkel Corporation  
Aerospace  
2850 Willow Pass Road  
P.O. Box 312  
Bay Point, CA 94565 USA  
**925.458.8000**  
Fax: 925.458.8030  
www.aerospace.henkel.com

### Description

Plastilock® 795-SF (PL 795-SF) is a modified epoxy film specifically formulated to improve the surface appearance on composite honeycomb structures. PL 795-SF may be cured at 250°F (121 °C) or 350°F (177 °C).

### Features

- Dual cure capabilities 250°F (121 °C) or 350°F (177 °C) eliminates the need for multiple surfacing films based on processing temperatures
- Designed to reduce surface imperfections including pinholes and core mark-off on composite sandwich panels. Results in improved surface appearance, less labor-intensive finishing operations, and weight minimization by reducing/eliminating repetitive applications of pinhole filler.
- Industry accepted; provides high quality surface versus other films typically used in surfacing applications
- Non-metallic filled version of PL 795
- Excellent out time - over 100 days @ 77°F (25 °C)
- Outstanding tack and handling characteristics: good building tack, yet repositionable on itself or pre-pregs
- Excellent hot-wet durability
- Minimizes core crush phenomenon
- Sandable and machine-able
- Minimal weight addition to composite structure

Typical Technical Data	PL 795-SF
Type:	Modified epoxy supported film
Scrim:	Non-woven polyester mat (other scrims available upon request)
Weight:	.03 ± .005 lbs/square foot (146 ± 24 g/SM)
Color:	Cream
Width:	Up to 48" wide (1.2m)
Volatiles:	<1.5% Max
Out Time:	100 + days @ 77°F (25 °C)
Shelf Life:	1 year @ 0°F (-18 °C)
Gel Time @ 250°F (121 °C):	10 - 25 minutes
Gel Time @ 350°F (177 °C):	1 - 3 minutes
% Flow @ 250°F (121 °C):	40 - 70
% Flow @ 350°F (177 °C):	40 - 70

Typical technical data and performance properties given for reference only. Not for specification purposes.

### Application Method

Remove PL 795-SF from freezer storage. Allow PL 795-SF surfacing film to reach room temperature before opening poly bag to prevent moisture contamination. Bonding surface should be clean, dry and free of contamination.

Remove poly liner and apply this side of surfacing film to the treated tool surface. Remove remaining liner and continue lay-up of pre-preg on to the surfacing film in your normal manner and cure appropriately.

### Curing

60 Minutes @ 350°F(177°C) and 25-100 psi (.17 - .69 MPa).

90 Minutes @ 250°F(121°C) and 25-100 psi (.17 - .69 MPa)

### Clean-up

Uncured surfacing film may be removed effectively with ketone solvents in well-ventilated areas. Avoid contaminating uncured parts. Consult solvent container label/ MSDS for proper safety and handling procedures.

### Storage

PL 795-SF has a shelf life of over 1 year at 0°F (-18°C).

PL 795-SF has an out time at 77°F (25°C) of over 100 days.

### Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood.

For industrial use only.

### General:

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty containers retain product residue and vapors so obey all precautions when handling empty containers.

ONE PART

**CAUTION!** This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

Plastilock® is a registered trademark of Henkel Corporation.

Rev. 6/05

---

**DISCLAIMER:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environmental and use. All data is subject to change as Henkel deems appropriate.

Users should review the Materials Safety Data Sheet (MSDS) and product label for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the MSDS and label are available upon request.

---

